



YC GROUP

<https://www.ycgroup.tw>
<https://www.achem.com.tw>



 Superior Grade	 Product No.	 Thickness mm(mils)	 Backing mm(mils)	 Adhesion kg/cm(oz/in)	 Holding Power (mins)	 Elongation (%)	 Tensile Strength kg/cm(lbs/in)	 Application Temperature°C(°F)	 Service Temperature°C(°F)	 RoHS	 REACH
	H2D10	0.032(1.26)	0.020(0.79)	0.36(31.75)	6000↑	140	2.6(14.3)	7°C~40°C 45°F~104°F	0°C~50°C 32°F~122°F	⊙	⊙
	H2F10	0.035(1.38)	0.022(0.87)	0.36(31.75)	6000↑	140	2.8(15.4)	5°C~40°C 41°F~104°F	-5°C~50°C 23°F~122°F	⊙	⊙
	H2790	0.038(1.5)	0.025(0.98)	0.36(31.75)	6000↑	140	2.8(15.4)	5°C~40°C 41°F~104°F	-5°C~50°C 23°F~122°F	⊙	⊙
	H27B0	0.040(1.57)	0.025(0.98)	0.36(31.75)	6000↑	140	2.8(15.4)	7°C~40°C 45°F~104°F	0°C~50°C 32°F~122°F	⊙	⊙
	H28A0	0.043(1.69)	0.028(1.1)	0.36(31.75)	6000↑	140	3.6(19.8)	7°C~40°C 45°F~104°F	0°C~50°C 32°F~122°F	⊙	⊙
	H2890	0.045(1.77)	0.028(1.1)	0.40(35.27)	10000↑	140	3.6(19.8)	5°C~40°C 41°F~104°F	-5°C~50°C 23°F~122°F	⊙	⊙
	H28F0	0.045(1.77)	0.028(1.1)	0.40(35.27)	6000↑	140	3.6(19.8)	7°C~40°C 45°F~104°F	0°C~50°C 32°F~122°F	⊙	⊙
 Low Temperature	H2500	0.070(2.76)	0.050(1.97)	0.40(35.27)	8000↑	180	5.2(28.6)	7°C~40°C 45°F~104°F	0°C~50°C 32°F~122°F	⊙	⊙
 Low Temperature	 Product No.	 Thickness mm(mils)									

