

Tel: 562-802-0998 • 800-213-3321 Fax: 800-509-8273 • 562-802-5069

Double Sided Foam Tape – DF F6X64

| Product Description | Double sided PE foam tape Coated on both sides with high performance acrylic adhesive Provides good initial tack and high adhesion to a variety of surfaces | | |
|--------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------|--------------------------|
| Technical Performance | Adhesive Type | Solvent-based acrylic adhesive | |
| | Carrier | Closed cell cross-linked PE foam | |
| | Tape | $1.5 \text{mm} \pm 0.02 \text{mm}$ (1/16" \pm 0.8 \text{ mil}) | Test method: PSTC-33 |
| | Liner | 0.070 mm ± 0.010 mm $(3.0$ mil ± 0.4 mil) | Test method: PSTC-33 |
| | Adhesion to steel | 2.0 kg/25mm (70 oz./in) | Test method: PSTC-01 |
| | 80°C Cohesion | 1440 minute † | Test method: PSTC-7 |
| | Elongation at break | 100% | Test method: PSTC-131 |
| | Service Temperature | -20 °C ~ 100 °C (-4 °F ~ 212 °F) | |
| Color | Tape Color | White | |
| | Release Liner Color | White Paper | |
| Storage Details | Shelf life recommended 6 months from the date of dispatch at the moderate temperature and humidity environment | | |

Note to Buyer/User: All statements, information, and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. The technical information and data obtained from tests are considered representative and should not be used for specification purposes recommended by PSTC. Before using, buyer/user shall determine suitability of the product for the product for its intended use and buyer/user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement, or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.