

## Double Sided Tape – DL 64H

<b>Product Description</b>	<ul style="list-style-type: none"> <li>Premium grade, double sided polyethylene terephthalate (PET) film tape</li> <li>Two sided coating of acrylic-based, pressure sensitive adhesives</li> </ul>		
<b>Application</b>	<ul style="list-style-type: none"> <li>Permanent bonding of materials such as metal, wood, plastic, paper, glass, ceramics and rubber</li> <li>Ideal for laminating plastic extrusions, especially PVC extrusions, for permanent mounting in the furniture industry</li> <li>Mounting of decorative parts and trims</li> </ul>		
<b>Features/Benefits</b>	<ul style="list-style-type: none"> <li>High quality and strong holding power acrylic adhesive allows for use on wide variety of surfaces</li> <li>Excellent resistance to heat, weathering and thermal creep</li> <li>Heavy-duty release paper allows for easy manual handling</li> <li>No known hazards</li> <li>Application Temperature: -20 °C to 80 °C (-4 °F to 176 °F)</li> </ul>		
<b>Technical Performance</b>	Tape thickness	0.13 mm (5.1 mil)	Test method: PSTC-133
	Adhesion to steel	0.47 kg/cm (42 oz./in)	Test method: ASTM D-1000
	23 °C Cohesion to steel	>1,440 minutes	Test method: PSTC-7
	Elongation at break	40%	Test method: PSTC-131
	Tensile strength	3.0 kg/cm (16.8 lb./in)	Test method: PSTC-131
<b>Storage Details</b>	Recommended one year shelf life from the date of dispatch at the moderate temperature and humidity environment		

Note to Buyer/User: All statements, information, and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. The technical information and data obtained from tests are considered representative and should not be used for specification purposes recommended by PSTC. Before using, buyer/user shall determine suitability of the product for the product for its intended use and buyer/user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement, or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.