

## ***Clear Advantage™* Selfwound Overlamination Film**

Product Description	#218 Clear Polypropylene, Heavy Coating Weight				
Construction	Film	Adhesive	Overall Thickness	Film Thickness	Adhesive Thickness
	Biaxially Oriented Polypropylene	Emulsion Acrylic	1.8 mil	1.0 mil ± 3%	0.8 mil ± 3%
Physical Properties	Note: The following technical information and data should be considered representative or typical only.				
	Tensile Strength		13.2 lbs/in		
	Elongation at Break		110%		
	180 <sup>o</sup> Peel Adhesion		18 oz/in		
Special Features	<ul style="list-style-type: none"><li>• Resistant to UV light</li><li>• Excellent resistance to chemical and abrasion</li></ul>				
Temperature Range	Application Temperature		Operating Temperature		
	32 <sup>o</sup> F to 150 <sup>o</sup> F		0 <sup>o</sup> F to 300 <sup>o</sup> F (nominal range)		
Web Width	60.5”				
Standard Length	5,000’				
Regulatory Compliance	21 CFR 177.1520, 21 CFR 175.105, RoHS, RoHS2, REACH, TSCA, Toy Safety Standard ASTM F963, ASTM-D-5486, CEPA, CONEG, Lacey Act, California Proposition 65, BPA Free, Bio Compatibility, CONEG Model, and “Conflict Mineral” Free				

Note to Buyer/User: All statements, information, and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. The technical information and data obtained from tests are considered representative and should not be used for specification purposes recommended by PSTC. Before using, buyer/user shall determine suitability of the product for the product for its intended use and buyer/user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement, or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.