

***Clear Advantage™* Selfwound Overlamination Film**

| | | | | | |
|-----------------------|---|------------------|--------------------------------|----------------|--------------------|
| Product Description | #220 Clear Polypropylene, Heavy Duty Film & Coating Weight | | | | |
| Construction | Film | Adhesive | Overall Thickness | Film Thickness | Adhesive Thickness |
| | Biaxially Oriented Polypropylene | Emulsion Acrylic | 2.2 mil | 1.2 mil ± 3% | 1.0 mil ± 3% |
| Physical Properties | Note: The following technical information and data should be considered representative or typical only. | | | | |
| | Tensile Strength | | 24 lbs/in | | |
| | Elongation at Break | | 150% | | |
| | 180° Peel Adhesion | | 20 oz/in | | |
| Special Features | <ul style="list-style-type: none">• Resistant to UV light• Excellent resistance to chemical and abrasion | | | | |
| Temperature Range | Application Temperature | | Operating Temperature | | |
| | 32° F to 150° F | | 0° F to 300° F (nominal range) | | |
| Web Width | 60.5” | | | | |
| Standard Length | 5,000’ | | | | |
| Regulatory Compliance | 21 CFR 177.1520, 21 CFR 175.105, RoHS, RoHS2, REACH, TSCA, Toy Safety Standard ASTM F963, ASTM-D-5486, CEPA, CONEG, Lacey Act, California Proposition 65, BPA Free, Bio Compatibility, CONEG Model, and “Conflict Mineral” Free | | | | |

Note to Buyer/User: All statements, information, and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. The technical information and data obtained from tests are considered representative and should not be used for specification purposes recommended by PSTC. Before using, buyer/user shall determine suitability of the product for the product for its intended use and buyer/user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement, or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.