

MK803 General Purpose Masking Tape

| | | |
|-------------------------------|---|---|
| Product Description | <ul style="list-style-type: none"> • Adhesive tape manufactured with crepe paper and pressure sensitive • High adhesion and rubber-resin adhesive • Very conformable, good tensile strength and strong holding | |
| Construction | Backing | Crepe Paper |
| | Adhesive | Rubber - Resin |
| | Color | Pale |
| Physical Properties | Note: The following technical information and data should be considered representative or typical only. | |
| | Total Thickness | 0.124 ± 0.015 mm (4.9 ± 0.59 mil) |
| | Adhesion to steel | ≥ 650g/inch (≥ 22.9 oz/in) |
| | Cohesion | ≥ 48 hours, 23° C (73° F) |
| | Tensile Strength | ≥ 8.93 kg/25 mm (≥ 20 lb/in) |
| | Elongation at Break | 10±4% |
| | Tack | ≤ 10 cm (3.94 in) |
| | Standard Width | 12 mm, 18mm, 24mm, 36mm, 48mm, 72mm |
| | Core Size | 72 mm (3 in) |
| Available Sizes | Length | 55 M |
| | Storage | Store in a clean, dry place. Temperature of 40°~80° F (4°~ 26° C) and 40%~ 50% relative humidity are recommended. |
| | Application | 40°~176° F (4°~80° C) |
| Temperature Conditions | Max Temperature resistance | 176° F (80° C) |

Note to Buyer/User: All statements, information, and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. The technical information and data obtained from tests are considered representative and should not be used for specification purposes recommended by PSTC. Before using, buyer/user shall determine suitability of the product for the product for its intended use and buyer/user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement, or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.