

13226 Alondra Blvd., Cerritos, CA 90703 • www.achem-usa.com Tel: 562-802-0998 • 800-213-3321 Fax: 800-509-8273 • 562-802-5069

## MK803 BLUE PAINTER'S GRADE

<b>Product Description</b>	<ul> <li>Adhesive tape manufactured with crepe paper and pressure sensitive</li> <li>High adhesion and rubber-resin adhesive</li> <li>Painter's tapes resist direct sunlight; hold up to 14 days with clean removal</li> </ul>	
Construction	Backing	Crepe Paper
	Adhesive	Rubber - Resin
	Color	Blue
Physical Properties	Note: The following technical information and data should be considered representative or typical only.	
	Total Thickness	$0.130 \pm 0.015 \text{ mm } (5.12 \pm 0.59 \text{ mil})$
	Adhesion to steel	≥ 450g/inch (≥ 15.9 oz/in)
	Tensile Strength	≥ 5.3kg/15 mm (≥ 19.8 lb/in)
	Elongation at Break	10±3%
	Tack	$\leq 10 \text{ cm } (3.94 \text{ in})$
	UV Resistance	14 days
	Release Force	350 ~ 650 (g/inch)
	Standard Width	12 mm, 18mm, 24mm, 36mm, 48mm, customized
	Core Size	72 mm (3 in)
	Length	55 M, customized
Temperature Conditions	Range	Temperature of $40^{\circ} \sim 80^{\circ}$ F ( $4^{\circ} \sim 26^{\circ}$ C) and $40\% \sim 50\%$ relative humidity are recommended.
	Application	40°~203° F (4°~95° C)
Storage	Storage	Jumbo or finished rolls on vertical position stored without direct sun contact. In room temperature of 23±2°C and humidity of 50±5%.
	Shelf Life	12 months, starting from estimated arrival date (ETA)

Note to Buyer/User: All statements, information, and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. The technical information and data obtained from tests are considered representative and should not be used for specification purposes recommended by PSTC. Before using, buyer/user shall determine suitability of the product for its intended use and buyer/user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement, or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.