

13226 Alondra Blvd., Cerritos, CA 90703 • www.achem-usa.com Tel: 562-802-0998 • 800-213-3321 Fax: 800-509-8273 • 562-802-5069

BS24 Bag Sealing Tape

	I	
Product Description	 PVC film, single sided packaging tape Suitable for use on standard and most recycle cartons Several advantages show performing at low temperature Good adhesion in several applications Good elongation and hand tear able 	
Construction	Backing	PVC Film
	Adhesive	Natural Rubber
	Color	Available in several colors
Physical Properties	Note: The following technical information and data should be considered representative or typical only.	
	Total Thickness	$0.059 \pm 0.005 \text{ mm } (2.36 \pm 20 \text{ mil})$
	Backing Thickness	$0.037 \pm 0.003 \text{ mm } (1.46 \pm 0.12 \text{ mil})$
	Adhesion to steel	$\geq .46 \text{ kg/}0.25 \text{ mm } (\geq 16.2 \text{ oz/in})$
	Cohesion	≥ 48 hours, 23° C (73° F)
	Tensile Strength	≥ 12.7 kg/25 mm (≥ 28 lb/in)
	Elongation at Break	≥ 70%
	Tack	≤ 5 cm (2 in)
	Unwind	$\leq 0.30 \text{ kg/}25 \text{ mm } (\leq 10.75 \text{ oz/in})$
Available Sizes	Standard Width	48 mm (2 in) & 72 mm (3 in)
	Core Size	72 mm (3 in)
	Length	9 M, 18 M, 24 M, 36 M, 48 M
Temperature Conditions	Storage	Product shelf life 12 months, based on the product being stored at 23° C (73° F), 50% relative humidity out of direct sunlight
	Application	32°~104° F (0°~40° C)
	Operating	32°~176° F (0°~80°C)

Note to Buyer/User: All statements, information, and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. The technical information and data obtained from tests are considered representative and should not be used for specification purposes recommended by PSTC. Before using, buyer/user shall determine suitability of the product for its intended use and buyer/user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement, or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.