

CS18A Tape

| | | |
|-------------------------------|---|--|
| Product Description | <ul style="list-style-type: none"> • Production grade pressure sensitive Carton Sealing Tape • Generally is used for box sealing applications • Construction provides a good closure for lightweight boxes exposed to minimal distribution hazards | |
| Construction | Backing | Biaxially oriented polypropylene film |
| | Adhesive | Water-based acrylic |
| | Color | Clear & Tan |
| Physical Properties | Note: The following technical information and data should be considered representative or typical only | |
| | Total Thickness | 0.045 ± 0.002 mm (1.77 ± 0.08 mil) |
| | Backing Thickness | 0.025 ± 0.001 mm (0.98 ± 0.04 mil) |
| | Adhesion to steel | ≥ 0.56 kg/25 mm (≥ 20 oz/in) |
| | Cohesion | ≥ 48 hours, 73° F (23° C) |
| | Tensile Strength | ≥ 7.14 kg/25 mm (≥ 16 lb/in) |
| | Elongation at Break | ≥ 150% |
| | Tack | ≤ 5 cm (2 in) |
| | Unwind | ≤ 0.57 kg/25 mm (≤ 20.43 oz/in) |
| | | |
| Available Sizes | Standard Width | 48 mm (2 in) & 72 mm (3 in) |
| | Core Size | 72 mm (3 in) |
| | Length | 50 M, 100 M, 914 M (55 yd, 110 yd, 1000 yd) |
| Temperature Conditions | Storage | Store in a clean, dry place. Temperature of 40°~80° F (4°~ 26° C) and 40%~ 50% relative humidity are recommended |
| | Application | 41°~104° F (5°~40° C) |
| | Operating | 32°~176° F (0°~80°C) |

Note to Buyer/User: All statements, information, and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. The technical information and data obtained from tests are considered representative and should not be used for specification purposes recommended by PSTC. Before using, buyer/user shall determine suitability of the product for the product for its intended use and buyer/user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement, or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.