

13226 Alondra Blvd., Cerritos, CA 90703 • www.achem-usa.com Tel: 562-802-0998 • 800-213-3321 Fax: 800-509-8273 • 562-802-5069

LP16A Label Protection Tape

	Ultra clear polypror	whene film coated with a clear acrylic adhesive
Product Description	 Ultra clear polypropylene film coated with a clear acrylic adhesive Remains clear even after long aging. Applied over shipping labels Product assures that the info on the label is not rubbed off 	
Construction	Backing	Biaxially oriented polypropylene film
	Adhesive	Water-based acrylic
	Color	Clear
Physical Properties	Note: The following technical information and data should be considered representative or typical only.	
	Total Thickness	$0.040 \pm 0.002 \text{ mm } (1.57 \pm 0.08 \text{ mil})$
	Backing Thickness	$0.023 \pm 0.001 \text{ mm } (0.91 \pm 0.04 \text{ mil})$
	Adhesion to steel	$\geq 0.50 \text{ kg/}25 \text{ mm} \ (\geq 18 \text{ oz/in})$
	Cohesion	≥ 48 hours, 23° C (73° F)
	Tensile Strength	≥ 8.03 kg/25 mm (≥ 18 lb/in)
	Elongation at Break	≥ 150%
	Tack	≤ 5 cm (2 in)
Available Sizes	Standard Width	72 mm, 96 mm, 120 mm, 140 mm
	Core Size	72 mm (3 in)
	Length	66 M (72 yd)
Temperature Conditions	Storage	Store in a clean, dry place. Temperature of $40^{\circ} \sim 80^{\circ}$ F ($4^{\circ} \sim 26^{\circ}$ C) and $40\% \sim 50\%$ relative humidity are recommended.
	Application	35°~104° F (1°~40°C)

Note to Buyer/User: All statements, information, and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. The technical information and data obtained from tests are considered representative and should not be used for specification purposes recommended by PSTC. Before using, buyer/user shall determine suitability of the product for its intended use and buyer/user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement, or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.